



MSR DC S

SILICON BASED POLYMER

TECHNICAL SHEET 22/11/2023

KEY FEATURES

- Sandable after curing
- Excellent temperature resistance
- High UV-resistance and chemical resistance

DESCRIPTION

Bostik MSR Deck Caulk S is a 1-component, silicon based, permanently elastic, fast curing sealant specifically developed for deck caulking applications in the yacht and boat building industry.

APPLICATIONS

- Bostik MSR Deck Caulk S is designed for watertight sealing of seams in teak decks and other decking materials.

FEATURES

- Excellent UV-resistance and ageing properties; Excellent resistance against fresh and salt water
- Product can be sanded after curing
- Solvent and isocyanate free
- High chemical resistance

TECHNICAL DATA

CHARACTERISTIC		VALUE
Basic material		Silicone Polymer
Curing method		Moisture
Specific gravity	[g/ml]	ca. 1.3
Skin forming time 23°C/50% R.H.	[min]	10
Curing speed after 24hrs 23°C/50% R.H.	[mm]	ca. 2
Shore A hardness		ca. 28
Weight Loss	[%]	ca. 5
Tensile stress (100%) ISO 37 (dumbbells)	[MPa]	ca. 0.5
Tensile stress at break ISO 37 (dumbbells)	[MPa]	ca. 1.1
Elongation at break ISO 37 (dumbbells)	[%]	ca. 450
Shear stress ISO 4587	[MPa]	ca. 1.0
Temperature resistance	[°C]	-40 to +110*
Application temperature	[°C]	+ 5 to +40
UV and weather resistance		Excellent
Colours (standard)		Black, Grey
Packaging		290ml cartridge 600ml sausage 200l drum

* = 10 Cycles of 7 hours at 100°C followed by 17 hours at 23°C/50%RH.

ADHESION

To obtain an excellent bonding on teak wood, a clean, dry and grease-free surface is required. The teak wood should be cleaned with Bostik Cleaner E and allowed to dry for a minimum of 5 minutes. Bostik MSR DC S can be applied immediately after drying.

For optimal use of MSR DC S's high elasticity, a minimum joint dimension relative to the width of the deck is recommended.

METHOD OF USE

For specific application instructions consult the Bostik instruction brochure "Application manual for bonding & caulking of teak decks"

Bostik MSR DC S can easily be extruded with a hand or air pressure gun at temperatures between +5°C and +35°C. Bostik MSR DC S should tooled or smoothed within 15 minutes (at 23°C/50% R.H.) of applying MSR DC S.

A minimum adhesive thickness of 2 mm is recommended.

In sealing applications, MSR DC S should be tooled or smoothed within 15 minutes (at 23°C/50% R.H.) using a spatula or putty knife, occasionally moistened with a soap solution.

Ensure to avoid soap solution penetrating between joint surface and adhesive, as this will cause loss of adhesion.

Cleaning tools or removing uncured residue of MSR DC S can be done with a clean colourless cloth, wetted with Bostik Liquid 1 or Bostik Cleaner E

Cleaning of Teak Decks:

See separate instruction brochure "Application manual for bonding & caulking of teak decks". In order to keep the teak decks in optimum shape we recommend cleaning with (salt) water or diluted pH neutral green soap and a soft brush. The brush must be used in a parallel direction to the teak planks. After cleaning the deck should be flushed with abundant fresh or salt water to remove excess soap.

We strictly advise against the use of detergents, cleaners and other chemicals as they may affect the deck caulk. Note that the use of high pressure cleaning equipment can severely damage the deck and deck caulk.

STORAGE

MSR Deck Caulk S can be stored for 18 months in cartridge and 12 months in sausage, in original unopened container in a dry place at temperatures between +5°C and +30°C.

FURTHER INFORMATION

The following publication is available on request:

- Material Safety Data Sheets (MSDS).

SMART HELP

Please contact your local representative



DISCLAIMER

Bostik offers this Technical Data Sheet ("TDS") for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations.

The statements, technical information, data, and recommendations contained in this TDS are provided 'AS IS' and are not warranted or guaranteed in any way. They represent typical results for the products and are based on Bostik's research only. Since the conditions and methods of use of the products are beyond our control, Bostik expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contained herein.

Bostik S.A.
Colombes, France
Phone : +33 (0)1 49 00 90 00
www.bostik.fr

Bostik Ltd.
Stafford, UK
Phone : +44 (0) 1785 27 27 27
www.bostik.co.uk

Bostik GmbH
Borgholzhausen, Germany
Phone : +49 (0)54 25/801-0
www.bostik.de

Bostik B.V.
Oosterhout, The Netherlands
Phone : +31 (0)162 491 000
www.bostik.nl

All advice, recommendations, figures and safety regulations provided are based on careful investigations, as well as the current state of our experience and are without obligation. Although the documentation has been compiled with the greatest care, we do not accept any liability for inaccuracies, mistakes, typesetting or printing errors. We reserve the right to modify the respective product if we deem it necessary. Since the design, the quality of the substrate and the processing conditions are beyond our assessment, no liability can be accepted for work performed on the basis of this documentation. We therefore advise you to carry out practical tests on site yourself. Our general Terms and Conditions of Sale and Delivery apply to all our sales and deliveries.